

CONTENTS

1.	On JSR RB	1
1-1	What is JSR RB?	1
1-2	Outstanding Features and Typical Applications of JSR RB	1
2.	Basic Properties of JSR RB	2
2-1	Dynamic Properties of JSR RB	2
2-1-1	Tensile Properties	2
2-1-2	Changes in Tensile Properties	2
2-1-3	Modulus	3
2-2	Thermal Properties of JSR RB	3
2-3	Molten Properties of JSR RB	4
2-3-1	Flow Curve·Viscosity Curve	4
2-3-2	Temperature Dependency of Flow	4
2-3-3	Barus Effect	5
2-4	Optical Properties of JSR RB	5
2-5	Electrical Properties of JSR RB	6
2-6	Chemical Resistance of JSR RB	6
2-7	Chemical Properties of JSR RB	7
2-8	Ease of Combustion of JSR RB	7
3.	Typical Physical Properties of JSR RB (Non Crosslinked)	8
4.	Application of JSR RB	9

Attention for processing JSR RB

1. Process and mold JSR RB below 150°C (resin temperature).
When it is processed between 150~180°C, do not keep it in the extruder for more than 10 minutes.
There is a possibility of gelation or fire when resin temperature is above 150°C.
2. Do not keep JSR RB in the extruder for more than two hours, even if resin temperature is below 150°C.
In case of discontinuation of manufacturing, purge the extruder with polyethylene, and stop heating.
3. After processing, purge the extruder with polyethylene.